

## Strenx® 1300 E/F

### General Product Description

Strenx® 1300 E/F is an ultra-high-strength structural steel with a minimum yield strength of 1300 MPa.

Typical applications include load-carrying structures that place very high demands on low weight. SSAB developed Strenx® 1300 E/F for building the lightest possible steel solutions or providing an alternative to other materials.

Strenx® 1300 E/F benefits include:

- Superior bendability and surface quality
- Weldability with excellent HAZ strength and toughness
- Exceptional consistency within a plate guaranteed by close tolerances
- High impact toughness which provides for good resistance to fractures

### Dimension Range

Strenx® 1300 E/F is available in plate thicknesses of 4.0 – 15.0 mm. Strenx® 1300 E/F is available in widths up to 2900 mm and lengths up to 14630 mm depending on thickness. More detailed information on dimensions is provided in the dimension program.

### Mechanical Properties

Thickness (mm)	Yield strength R <sub>p0.2</sub> (min MPa)	Tensile strength R <sub>m</sub> (MPa)	Elongation A <sub>5</sub> (min %)
4.0 - 15.0	1300	1400 - 1700	8

For transverse test pieces.

### Impact Properties

Product	Min impact energy for transversal testing, Charpy V 10x10 mm test specimen <sup>1)</sup>
Strenx® 1300 E	27 J / -40 °C
Strenx® 1300 F	27 J / -60 °C

<sup>1)</sup> Unless otherwise agreed, transverse impact testing according to EN 10025-6 option 30 will apply. For thicknesses between 6 - 11.9 mm, sub-size Charpy V-specimens are used. The specified minimum value is then proportional to the cross-sectional area of the specimen compared to a full-size specimen (10 x 10 mm).

### Chemical Composition (ladle analysis)

C <sup>*)</sup> (max %)	Si <sup>*)</sup> (max %)	Mn <sup>*)</sup> (max %)	P (max %)	S (max %)	Cr <sup>*)</sup> (max %)	Cu <sup>*)</sup> (max %)	Ni <sup>*)</sup> (max %)	Mo <sup>*)</sup> (max %)	B <sup>*)</sup> (max %)
0.25	0.50	1.40	0.010	0.003	0.80	0.30	3.0	0.70	0.005

The steel is grain refined. <sup>\*)</sup> Intentional alloying elements.

### Carbon Equivalent CET(CEV)

	Thickness (mm)	4.0 - 15.0
Strenx® 1300 E	Max CET(CEV)	0.43 (0.67)
Strenx® 1300 F	Max CET(CEV)	0.43 (0.67)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40} \quad CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

## Tolerances

More details are given in SSAB's brochure Strenx® Guarantees or on [www.ssab.com](http://www.ssab.com).

## Thickness

Tolerances according to Strenx® Thickness Guarantees.

Strenx® Guarantees meet the requirements of EN 10029 Class A, but offers narrower tolerances.

## Length and Width

According to SSAB's dimension program. Tolerances conforms with EN 10029.

## Shape

Tolerances according to EN 10029.

## Flatness

Tolerances according to Strenx® Flatness Guarantee Class D, which are more narrow than EN 10029 Class N.

## Surface Properties

According to EN 10163-2 Class A, Subclass 3.

## Delivery Conditions

The delivery condition is Quenched and Tempered. The plates are delivered with sheared or thermally cut edges. Untrimmed edges after agreement.

Delivery requirements can be found in SSAB's brochure Strenx® Guarantees or on [www.ssab.com](http://www.ssab.com).

## Fabrication and Other Recommendations

### Welding, bending and machining

Recommendations are found in SSAB's brochures at [www.ssab.com](http://www.ssab.com) or consult Tech Support.

Strenx® 1300 E/F has bending guarantees according to Strenx® Bending Guarantees Class D.

Strenx® 1300 E/F has obtained its mechanical properties by quenching, and at our discretion, subsequent tempering. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 200°C.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.

## Contact Information

[www.ssab.com/contact](http://www.ssab.com/contact)